

► Ghemco FAE

FIBERED ASPHALT EMULSION

► The Brand
You can Trust!

GHEMCO FAE is a fiber reinforced water based roof and waterproof coating that is solvent free. Ideal for use as a surface coating for built-up roofing, metal, masonry surfaces, and for pipes and tanks above or below ground level. Will not run, sag, crack, or "alligator" under most weather conditions. Meets and exceeds all the requirements of ASTM D 1227, Type II, Class I.

DIRECTION OF USE

Preparation

All surfaces must be clean, have proper drainage, and be free from rust, dirt, and all other foreign matter. Clean all cracks, holes, and damaged areas, repairing when necessary and allow repairs to thoroughly cure.

Application

Apply Ghemco FAE by roofing brush, roller, or spray, evenly covering the surface. Two coats are recommended. Allow to dry completely between coats. Dry time is usually 6-24 hours in dry or hot weather conditions. In cool or damp weather drying will be slower, 2-7 days.

Coverage

Apply at the rate of approximately 3-4 gallons per 100 square feet per coat as a topical protective coating and 6-8 gallons total for restoration systems.

SAFETY & PRECAUTIONS

Precautions

DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Do not apply when ambient temperature is below 55°F or if temperatures fall below 40°F within 48 hours. Application over hot applied asphalt may not prevent alligating. This coating is not recommended over rubber, PVC sheet roofing, or old roofs that are too dry and brittle. When transporting this product, be sure the pail is secured and the lid is tight. Do not allow pail to tumble, as this may loosen the lid and allow leakage to occur.

Caution

DO NOT TAKE INTERNALLY! KEEP OUT OF REACH OF CHILDREN. Use protective measures to avoid contact with eyes and skin. If swallowed, CALL PHYSICIAN IMMEDIATELY! In case of eye contact, open eyelids wide and flush immediately with plenty of water for at least 15 minutes. GET MEDICAL ATTENTION! CAUTION! KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY! DO NOT USE IF RAIN IS IMMINENT - COATING MUST BE DRY BEFORE EXPOSURE TO WATER.

MAXIMUM V.O.C = 30 G/L

WATER SOLUABLE

BOILING POINT — 212°F

FLASH POINT — NONE

VAPOR DENSITY — HEAVIER THAN AIR