

▶ FabGhard

Fabrics

FabGhard is a 100% polyester reinforcement, stitch bond 2.98 oz fabric used in all deck coating systems, emulsion asphalt roof coatings, acrylic, silicone, urethane and all other elastomeric, liquid-applied roof coatings. FabGhard adds tremendous strength and reinforcement to any elastomeric liquid-applied roof coating system.

FEATURES & BENEFITS

FabGhard is designed to reinforce cracks, seams, joints, large openings, gaps, splits, and tears in any deck and roof system. Helps build strength in drains, scuppers, penetrations, transitions and flashing detail in all types of roof restoration systems.

DIRECTION OF USE

Storage & Handling

FabGhard is designed to reinforce cracks, seams, joints, large openings, gaps, splits, and tears in any deck and roof system. Helps build strength in drains, scuppers, penetrations, transitions and flashing detail in all types of roof restoration systems.

SAFETY & PRECAUTIONS

Safety

Use appropriate protective clothing, hand and eye protection. This product is intended for industrial use by properly trained professional applicators only. Do not use in food grade systems or potable water. Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying FabGhard in any systems, and/or any other elastomeric roof and decking system. Published technical data and instructions are subject to change without notice. Contact your local Ghemco representative.

TECHNICAL DATA

Fabric Weight	2.98 oz. / sq. yd.
Material Finish	100% Polyester (firm & soft)
Color	White
Bursting Strength	119 lbs. / sq. in.
Tear Strength (lbs.)	Warp 11.0 / Weft 21.25
Elongation (%)	Warp 20.05 / Weft 70.05
Tensile Strength / Breaking Strength (lbs.)	Warp 56.35 / Weft 44.80

FABRIC SIZES

4" x 324' (108 yards)
6" x 324' (108 yards)
12" x 324' (108 yards)
18" x 324' (108 yards)
40" x 324' (108 yards)

* This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will affect dry time. The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description. Product specifications and performance will vary depending on application methodologies, raw materials and other factors.

Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying material. Published technical data and instructions are subject to change with- out notice. Contact your local Ghemco Representative or visit our website for current technical data and instructions.

DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Ghemco makes no claim that these tests or any other tests, accurately represent all environments.